

Mixed-metal Ionothermal Synthesis of Metallophthalocyanine Covalent Organic Frameworks for CO₂ Capture and Conversion


K. Song¹, P. W. Fritz¹, D. F. Abbott², L. N. Poon², C. M. Caridade¹, V. Mougel^{2*}, A. Coskun^{1*}

¹Department of Chemistry, University of Fribourg, Fribourg 1700, Switzerland, ²Department of Chemistry and Applied Biosciences ETH Zürich Vladimir-Prelog-Weg 1-5, Zürich 8093, Switzerland

Phthalocyanines (PCs) are macrocyclic compounds containing nitrogen-bridge, and their chemical property and stability are tuned by the coordinated metal ions. The metallophthalocyanines (M-PCs) have been investigated in various chemical reactions including electrical-photochemical CO₂ reduction since the coordinated metal atom acts as a catalytic active site in the reaction. Therefore, their polymeric counterparts featuring extended conjugated backbones have gained significant interest as heterogeneous catalysts and PC-containing frameworks such as covalent organic frameworks (COFs) have been widely investigated for CO₂ capture and conversion [1].

General solvothermal reaction methods for PC-based frameworks cause low-crystallinity of frameworks due to the high stability of the linkers, and require an expensive catalyst, organic solvent, and additional work-up steps to purify it. Therefore, a novel and environmentally friendly synthetic approach for high crystallinity of PC-based frameworks is required.

Herein, we show the innovative synthesis strategy using the mixed metal salt (MCl₂/ZnCl₂, M = Cu²⁺, Ni²⁺, Co²⁺, and Fe²⁺) in the ionothermal synthesis of Phthalocyanine based Covalent Organic Frameworks (COFs) which called PPC (Porous polyphthalocyanines). We hypothesized that mixed metal salt mixtures (MCl₂/ZnCl₂) would result in PPC including desired metal ions, which has a higher complex stability than that of the Zn-phthalocyanine according to the Irving-Williams series, which predicts the relative stability of complexes formed by transition metals that increases when moving in the periodic table from Fe²⁺ to Cu²⁺. In the end, we found a clear correlation between the Irving-Williams series and the metal content, surface area, and CO₂ adsorption capabilities of PPCs. This result provides a tunable approach to designing these polymer properties. Noticeably, with surface areas as high as 2043 m²g⁻¹ and CO₂ uptake capacities up to 7.6 mmol g⁻¹, these polymers exhibit significant potential for CO₂ application. In addition, We also investigated the growth of the Co-pPPC and Co-anPPC on highly conductive carbon nanofibers and demonstrated their high catalytic activity in the electrochemical CO₂ reduction, which show Faradaic efficiencies towards CO of up to 74% at -0.64 V vs. RHE.



[1] Kyung Seob Song, Patrick W. Fritz, Ali Coskun, *Chem. Soc. Rev.*, **2022**, 51, 9831-9852